

Material name, short description	NBR
Material name, based on technical standards	Acrylic-Butadiene-Rubber
Material description / intended use	Elastomer with good resistance to mineral and vegetable oils/greases, alkalis, alcohols, gas, water
Color	black
Compound code	NBR 90.00-02
Old, but still valid compound code	NBR 90.315-02

**Mechanical properties**

Hardness nominal	90 $\pm$ 5 Shore A ASTM D 2240
Density nominal	1.3 $\pm$ 0.02 g/cm <sup>3</sup> ASTM D 297
Tensile strength	17.8 N/mm <sup>2</sup> ASTM D 412
Elongation at break	190 % ASTM D 412
Compression set	14 % ASTM D 395-B 22 h, 100 °C

**Thermal properties**

Operating temperature min.*	-30 °C
Operating temperature max.*	100 °C
TR 10 value	-19.9 °C ASTM D 1329

\* Approximate value, dependent on the application

**Storage in medium 1**

Medium	IRM 901 Oil (ASTM 1)
Test parameter	70 h, 100 °C
Test standard	ASTM D 471
Value change	Hardness: +1 Points Tensile strength: +2 % Elongation at break: -10 % Volume: -4 %

**Storage in medium 2**

Medium	IRM 903 Oil (ASTM 3)
Test parameter	70 h, 100 °C
Test standard	ASTM D 471
Value change	Hardness: -3 Tensile strength: -4 % Elongation at break: -13 % Volume: +8 %

**Air aging 1**

Test parameter	70 h, 100 °C
Test standard	ASTM D 573
Value change	Hardness: +1 Points Tensile strength: -3 % Elongation at break: -5 %

In compliance with **RoHS** and **REACH** directives.

This information is based on our available data. These values are measured on standard test specimens and are within the normal tolerance range of material properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. The customer is solely responsible for quality and suitability of material for his application. He has to test usage and processing prior to use. Angst+Pfister makes no guarantees for the suitability of the material for any given application and assumes no obligation or liability in connection with the information provided above.