

Application purpose and characteristics

Mechanical engineering, electrical and electronic industries, food industry

High chemical resistance, high dimensional stability, low moisture absorption, suitable for direct food contact

Material name, short description	POM-C
Material name, based on technical standards	Polyoxymethylene copolymer
Density	1.41 g/cm ³
Color	blue
Compound code	POM-C 00.001-02

Mechanical properties

Yield stress	67 N/mm ² DIN EN ISO 527
Elongation at rupture	30 % DIN EN ISO 527
Flexural modulus of elasticity	2800 N/mm ² DIN EN ISO 527
Hardness test value	81 Shore D
Notch impact strength	6.00 kJ/m ² DIN EN ISO 179

Electrical attributes

Comparative tracking index	600 IEC 60112
Dielectric dissipation factor 1	0.002 IEC 60250 50 Hz
Dielectric constant 1	3.8 IEC 60250
Dielectric strength 1	40 kV/mm IEC 60243
Surface resistivity	10 ¹³ Ω IEC 60093
Volume resistivity	10 ¹³ Ω*cm IEC 60093

Thermal attributes

Min. operating temperature	-50 °C
Max. operating temperature long term	100 °C
Max. operating temperature short term	140 °C
Coefficient of linear thermal expansion 1	110 * 10 ⁻⁶ /K DIN 53752
Crystalline melting point	165 °C ISO 11357-3
Heat deflection temperature 1	110 °C DIN EN ISO 75 / A
Specific heat capacity	1.5 J/(g·K) DIN 52612
Thermal conductivity	0.31 W/(m·K) DIN 52612-1

Other attributes

Moisture absorption	0.2 % DIN EN ISO 62
---------------------	------------------------

Approvals / Compliance

Food & Beverage	FDA CFR 21 - 177.2470 "Polyoxymethylene copolymer"
	FDA CFR 21 - 177.2470 "Polyoxymethylene copolymer" All type of food except food containing more than 15% or more alcohol
	EC No. 1935/2004 incl. last amendments



EC No.1935:2004



In compliance with **RoHS** and **REACH** directives.

This information is based on our available data. These values are measured on standard test specimens and are within the normal tolerance range of material properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. The customer is solely responsible for quality and suitability of material for his application. He has to test usage and processing prior to use. Angst+Pfister makes no guarantees for the suitability of the material for any given application and assumes no obligation or liability in connection with the information provided above.